



EVO-STIK Resin 'W' Polyurethane Wood Adhesive

MOISTURE CURING POLYURETHANE GEL PASTE

Date: 15 September 2015

Fact Sheet No.: TDS00148

YOUR SMART ADVANTAGES

- Excellent water resistance
- Cures rapidly
- Bonds many rigid porous and non-porous surfaces

USES

EVO-STIK Resin 'W' Polyurethane Wood Adhesive is based on a moisture curing, single part polyurethane resin system. It cures rapidly and joints can, generally, be carefully handled after just 5 minutes. It has excellent water resistance.

EVO-STIK Resin 'W' Polyurethane Wood Adhesive is ideal for bonding wood and many other hard, rigid and porous surfaces such as concrete, plaster and brick. It is also ideal for bonding many rigid non-porous materials such as metals, foamed polystyrene, GRP and PVC.

However, one of the surfaces being bonded must be porous. It will not bond to polythene (polyethylene), polypropylene, EPDM rubber, Teflon and some engineering plastics such as nylon. The product is not intended to be used as a sealant.

PRODUCT CHARACTERISTICS

Colour	Transparent
Form	Thixotropic paste
Specific Gravity	1.1 approx.
Composition	Polyurethane pre-polymer
Solids Content	100%
Product Code	30813226 310ml x 12

	30813228 500 ml x 12
Storage/Shelf Life	Store for up to 12 months from the date of manufacture when stored in original, unopened packaging under dry conditions within the temperature range of +5°C to +25°C.

TYPICAL PERFORMANCE DATA (Approx.)

Application Temperature	+10°C to +35°C
Clamping Time	5 minutes at 25°C but longer if colder or if the humidity is low.
Cure Time	90% of full cure in 24 hours at 25°C
Temperature Resistance	When cured: -30°C to +100°C
Flashpoint	> +100°C
Coverage	310ml: Up to 11 linear metres of 6mm diameter bead 500ml: Up to 18 linear metres of 6mm diameter bead

DIRECTIONS FOR USE

IMPORTANT: Before using EVO-STIK Resin 'W' Polyurethane Wood Adhesive refer to the relevant Health & Safety Data Sheet, available at www.bostik.co.uk.

PREPARATION

1. EVO-STIK Resin 'W' Polyurethane Wood Adhesive must only be used when one of the surfaces to be bonded is porous. Surfaces must be clean and free from any loose material or contamination such as grease etc.
2. Non-porous surfaces should be abraded to give a good key.



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk

Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

3. Porous surfaces should be moistened with water.
4. Ensure to protect any vulnerable surfaces during application.

APPLICATION

5. Apply thin beads to one of the surfaces and then carefully press the two together.
6. Lightly clamp the substrates to produce a thin bond-line.
7. In good conditions the bond can be lightly handled after 5 minutes. This time will be extended if the conditions are cool or dry. It will be greatly extended if excess adhesive is used.
8. Full cure will be achieved in about 24 hours at 25°C.

CLEANING

9. Removal of this adhesive is extremely difficult even when it is uncured. It is advisable to protect any vulnerable surfaces.

Uncured Adhesive:

10. Carefully scrape up excess adhesive and then remove the remains using acetone. It will be almost impossible to remove the uncured adhesive from cloths and porous or rough surfaces.

Cured Adhesive:

11. This can only be removed mechanically. The best time is when it has just cured.

PRECAUTIONS IN USE

EVO-STIK Resin 'W' Polyurethane Wood Adhesive must only be used when one of the surfaces to be bonded is porous. EVO-STIK Resin 'W' Polyurethane Wood Adhesive will not bond to polythene (polyethylene), polypropylene, EPDM rubber, Teflon and some engineering plastics such as nylon. The product is not intended to be used as a sealant.

Do not use excess adhesive as this will greatly extend the clamping time and also produce a weaker bond. Clamping is necessary because the curing process produces carbon dioxide as a by-product and this causes foaming which would lead to a very much weaker and less resistant bond.

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.co.uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data Sheet for EVO-STIK Resin 'W' Polyurethane Wood Adhesive, available at www.bostik.co.uk.

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk

Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	Fax: 01785 241818	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	Fax: 01785 272867	technical.service@bostik.com
Technical Data & COSHH (MSDS) Data Sheets	Tel: 01785 272625	Fax: 01785 212962	stafford.gatehouse@bostik.com



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk
Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.